

# Copper

## C101 / CW004A

Version 2

Reference standard: EN 13601

Symbol	Number	Element	Cu	Ag	Bi	O	P	Pb	Other	Density g/cm <sup>3</sup>
C101	CW004A	Min %	99.90	-	-	-	-	-	-	8.9
		Max %	-	-	0.005	0.040	-	0.005	0.03	

Single bare Electrolytic tough-pitch (ETP) Copper wire, manufactured in round, square and flat sections.

Typical Tensile Strength N/mm <sup>2</sup>			
Soft	¼ Hard	½ Hard	Hard
220-270	270-300	300-400	370min

### Physical Properties:

- Resistivity: 0.0172 ( $\Omega \times \text{mm}^2/\text{m}$ )
- Melting Point °C: 1083
- Elongation at soft temper: >30%
- Density: 8.9 kg/dm<sup>3</sup>

### Size Tolerances:

<0.25mm	±0.005mm
0.25-0.50mm	±0.008mm
0.50-1.00mm	±0.012mm
1.00-2.00mm	±0.02mm
2.00-4.00mm	±0.03mm

### Typical applications:

- Resistance wire
- Electrical and electronic components
- Industrial equipment such as HVAC systems
- Automotive wiring



Chaplin Bros. (Birmingham) Limited  
Reddicap Trading Estate  
Sutton Coldfield  
West Midlands  
B75 7BU, England

Tel: +44(0)121 378 0565  
Email: [sales@chaplinwire.com](mailto:sales@chaplinwire.com)  
[www.chaplinwire.com](http://www.chaplinwire.com)

