

Copper Nickel Alloys



CuNi6 / 2.0807 / C70500

Version 2

Reference standard: DIN 17471

Symbol	Element	Cu	Ni	Density g/cm ³
CuNi6	Min %	-	-	8.9
	Max %	Bal	6	

Physical Properties:

- Resistivity (soft): 0.0980 ($\Omega \times \text{mm}^2/\text{m}$)
- Temperature coefficient of resistance: 0.07 (%/K)
- Conductivity soft (MS / m): 10
- Elongation at soft temper: >25%
- Tensile strength soft: 320 N/mm²

Size Tolerances:

<0.25mm	±0.005mm
0.25-0.50mm	±0.008mm
0.50-1.00mm	±0.012mm
1.00-2.00mm	±0.02mm
2.00-4.00mm	±0.03mm

Typical applications:

- Resistance wire



Chaplin Bros. (Birmingham) Limited
Reddicap Trading Estate
Sutton Coldfield
West Midlands
B75 7BU, England

Tel: +44(0)121 378 0565
Email: sales@chaplinwire.com
www.chaplinwire.com

